



Stainless Steel Solid Wire

MIG/TIG Welding

AWS A5.9: ER308L
ISO 14343-A-2009 19 9 L

SW-308L

DESCRIPTION & APPLICATION

MIG/TIG Filler wire for the joining and overlay of Stainless Steels of similar composition such as AISI 304L. Low carbon content minimises Carbide precipitation.

BASE MATERIALS

All 300 series Austenitic Stainless Steel, Overlay of Mild Steel (Cladding)
Joining of Austenitic Manganese Steels (Hadfields).

MECHANICAL PROPERTIES

~600n/mm UTS n/mm	>380 YIELD 0.2%	>35 ELONG A5%	>40 CV (J) -196°C
----------------------	--------------------	------------------	----------------------

METAL WELD COMPOSITION %

C	Si	Mn	Cr	Ni	Mo	S	P	Fe
0.012	0.4	1.9	19.5	10.5	0.05	0.002	0.02	BAL

PACKAGING

15kg Spools (MIG)
5kg Tubes (TIG)

DIAMETERS

0.8, 1.0, 1.2mm (MIG)
0.8, 1.6, 2.4, 3.2mm (TIG)

WELDING INSTRUCTIONS

Shielding gas 5% or 20% CO₂ in Argon, or 2% Argon-Ox (MIG). 100% Argon (TIG). Do not allow the base material to overheat, maintain interpass temperature below 150°C.

Need Help?

01925 839983

sales@westbrookwelding.co.uk

Discover all our specification sheets to help you more:
westbrookwelding.co.uk