



Selectarc 25/20B

High Temperature
Stainless Steel Electrode

Classification

AWS A5.4 : E310-15 EN 1600 : E 25 20 B 4 2
ISO 3581-A : E 25 20 B 4 2

Description & Applications

Basic coated electrode with an austenitic stainless steel deposit resisting to corrosion and oxidation up to 1200°C. Regular and stable fusion, good slag removal, nice aspect of the bead, resistant against hot cracks.

Main applications: Ovens, boilers, thermal equipments for heat treatment, chemical and petrochemical installations.

Base materials

Stainless and high temperature steels:

UNS	Alloy	EN	Material N°	UGINE
S31000	310	X15CrNiSi25-20	1.4841	
S31008	310S	X12CrNi25-21	1.4845	UGINOX R 25-20
S31400	314	X15CrNiSi25-20	1.4841	
S30900	309	X15CrNiSi20-12	1.4828	UGINOX R 20-12
		G-X15CrNi25-20	1.4840	
J93503		G-X40CrNiSi25-12	1.4837	
J94204	HK40	G-X40CrNiSi25-20	1.4848	

Typical Weld Metal Composition (%)

C	Si	Mn	Cr	Ni	Fe
<0.12	0.5	2.2	25.5	20.5	Rem.

All Weld Metal Mechanical Properties


R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	KV (J)
>380	>550	>30	+20°C >70

Welding Current & Instructions

Electrode	ØxL (mm)	2,5x300	3,2x350	4,0x350	5,0x450
Current	(A)	70	100	135	180

Redrying 2 hours at 250°C, if necessary. Avoid long stay at 600-850°C (sigma phase formation).
Interpass temperature : < 150°C.

ind.12



Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.