



# Selectarc 54

*Rutile Electrode  
Nice appearance*

## Classification

AWS A5.1 : E6013

EN 499 : E 42 0 RR 1 2

ISO 2560-A : E 42 0 RR 1 2

## Description & Applications

Heavy coated rutile electrode for general use. Especially recommended for downhand welding, for fillet welds and vertical up position. Soft arc, few spatters, self lifting slag, excellent bead appearance.

**Main applications:** Currently used for welding mechanical constructions, shipbuilding, blacksmithing, boiler making...

### Base materials

### Construction steels for general use , Tube steels, Ship steels

EN- Designation	S185 – S355 P235 – P355	L210 – L360
Ship steels	Quality A and B	
ASTM	A285 grade C A442 grade 55, 60	A414 grade C, D, E, F A515 grade 55, 60, 65

## Typical Weld Metal Composition ( % )

C	Si	Mn	P	S	Fe
<0.10	0.4	0.6	<0.025	<0.025	Rem.


## All Weld Metal Mechanical Properties

R <sub>e</sub> ( MPa )	R <sub>m</sub> ( MPa )	A <sub>5</sub> ( % )	KV ( J )	
>400	510-580	>22	+20°C	>64
			0°C	>47
			-20°C	>28

## Welding Current & Instructions

Electrode	ØxL ( mm )	2,0x300	2,5x350	3,2x350	3,2x450	4,0x350	4,0x450	5,0x450
Current	( A )	55	70	115	115	150	150	180

Ind.12



= - ~ 45V

**Liability:** This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.