



Selectarc B68

*Basic coated Electrode
For creep resisting steels*

Classification

AWS A5.5 : E9018-B3 EN 1599 : E CrMo2 B 4 2 H5
ISO 3580-A : E CrMo2 B 4 2 H5

Description & Applications

Low hydrogen basic coated electrode alloyed with Cr and Mo for welding creep resisting steels used in service up to 600°C (including 2%Cr -1%Mo castings). High resistance to H₂S, ...

Main applications: For overheaters, valve bodies, pipes, boilers, hydrocrackers.

Base materials :

Tubes & steels for boiler and pressure vessels:

NF A 36-206	: 15CD4-05 – 10CD9-10
DIN 17155 and 17245	: 10 Cr Mo 9.10 – 10 Cr Si Mo V7
	: 24 CrMo V55 – 12 Cr Mo 9.10 GS 12 Cr MO 9.10...
BS	: 1501 Gr 622 to 1504 Gr 622, BS 359 Gr 622/640 1503 Gr 660, 1504Gr 660
ASTM	: A 387 GrD – A 335 GrP 22 – A 213 GrT 22, T36

Grade Vallourec: Chromesco 3

Typical Weld Metal Composition (%)

C	Si	Mn	Cr	Mo	P	S	Fe
0.07	0.4	0.8	2.25	1.0	<0.025	<0.025	Rem.

All Weld Metal Mechanical Properties *

R _e (MPa)	R _m (MPa)	A ₅ (%)	KV (J)
>450	>570	>17	+20°C >100



* After heat treatment at 700°C/1h

Welding Current & Instructions

Electrode	ØxL (mm)	2,5x350	3,2x350	4,0x450	5,0x450
Current	(A)	80	115	150	190

Redrying: 1h at 300°C, if necessary. Preheating of joints to weld at 250°C. Interpass temperature: 150-300°C. Annealing after welding is advised at 700-750°C/1h.

ind.12



Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.