



Selectarc B82

*Basic Electrode
For cold tough steels*

Classification

AWS A5.5 : E8018-C1 EN 499 : E 46 6 2Ni B 4 2 H5
ISO 2560-A : E 46 6 2Ni B 4 2 H5

Description & Applications

Low hydrogen basic coated electrode alloyed with Nickel for welding cold tough fine grain steels (steels with Nickel, heat treated steels) applied at low temperature -60°C. Good characteristics of cold toughness.

Main applications : For liquid gas distribution pipes, tanks, off shore, and petrochemistry.

Base materials

Fine grain construction steels, cold tough:

NF A 36-204	:	E420T – E460T
NF A 36-205	:	A37FP – A42FP – 48FP – A52FP
NF A 36-207	:	A510FP1 – A550FP2
NF A 36-208	:	0.5 Ni 285 and 355 (10N2) – 1.5 Ni 285 and 355 (15N6)
DIN 17102	:	TStE 255 to TStE 420
DIN 17780	:	14Ni6 – 10Ni14 – 11MnNi5.3 – 12MnNi6.3 – 13MnNi6.3.
ASTM	:	A203Cr A and B – A352CrLC2 – A334Cr7 – A714Cr 1 à 6 A707Cr L4 à L6 – A662Cr A and B

Typical Weld Metal Composition (%)

C	Si	Mn	Ni	P	S	Fe
<0.12	0.4	1.0	2.5	<0.025	<0.025	Rem.

All Weld Metal Mechanical Properties

R _e (MPa)	R _m (MPa)	A ₅ (%)	KV (J)	
>460	>550	>19	-40°C	>70
			-60°C	>30
			-73°C	>27



*After thermal stress relieving at 620°C/1h

Welding Current & Instructions

Electrode	ØxL (mm)	2,5x350	3,2x350	4,0x450	5,0x450
Current	(A)	80	115	150	190

Redrying at 350 °C during 1 hour if necessary. Eventual preheating of the welding joints (above 100 °C), in the case of heavy thickness.

ind.12



Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.