



# Selectarc B92Co

*Hardfacing Electrode  
Thermal shock resistant*

## Description & Applications

Special hardfacing electrode with 170% recovery and a deposit composition of alloy C (Ni-Cr-Mo) + Co. Rutile-basic coating with outstanding welding characteristics. Deposit resists against corrosion, scaling, oxidation and thermal shocks. It is machinable. Selectarc B92Co is used to surface parts subject to compression, corrosion, high temperatures (400-800°C) as well as thermal shocks. This electrode has a higher hot strength and is more resistant against thermal shocks and metallic abrasion compared to Selectarc B 92.

**General applications:** Surfacing of hot working tools, as hot shear blades, deburring tools, swages, forging saddles, forging and hot trimming dies, press tools as well as pump parts.

## All Weld Metal Mechanical Properties

Hardness (as welded)  
~250 HB

Hardness (work-hardened)  
350-400 HB

## Welding Current & Instructions

Electrode	ØxL ( mm )	2,5x350	3,2x350	4,0x350
Current	( A )	75	110	135

For heavier overlays use only for the last two cover passes. For intermediate layers use Selectarc B90 electrodes. Keep amperage low, preheat heavy workpieces to 300-500° C. Guide electrodes steep, keep arc short, and prevent excessive weaving. Workpiece should be kept at temperature during surfacing and then cooled down slowly.

ind.13



= + ~ 70V



**Liability:** This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.