



# Selectarc Fonte Fe3

Cast Iron Electrode  
For hot welding

## Classification

AWS A 5.15 : "ECI-B"

DIN 8573 : E FeC-G-BG 42

ISO 1071 : E C FeC-GF 3

## Description & Applications

Graphite basic coated electrode for hot welding nodular cast iron with a colour and structure matching deposit. Stable arc, can weld over hot slag, good bonding and flow of the weld metal.

**Main applications:** Used to weld defects in foundries.

### Base materials

#### Nodular cast iron:

ASTM	DIN	NFA
A536 Grade 60-40-28	GGG-40	FGS 400-12
	GGG-40.3	FGS 370-17
	GGG-50	FGS 500-7
A536 Grade 80-55-06	GGG-60	FGS 600-3
A536 Grade 100-70-03	GGG-70	FGS 700-2

## Typical Weld Metal Composition ( % )

C	Si	Mn	Fe
3.0	3.2	0.3	Rem.

## All Weld Metal Mechanical Properties

R <sub>p0.2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Hardness
320	450	15	220 HB

After PWHT 900°C/2h + 700°C/4h

## Welding Current & Instructions

Electrode	ØxL ( mm )	3,2x350	4,0x450	5,0x450	6,0x450
Current	( A )	110	150	180	250

Prepare the casting defect to be repaired, preheat the piece to 550-650°C, keep this temperature during welding, use a current as high as possible, without overheating the electrode. Assure that sufficient base metal is melted to get a good bonding. When welding over the hot slag don't move too fast with the arc to avoid trapped slag. After welding a PWHT, 2h at 900°C followed by 4h at 700°C and slow cooling in the furnace, insures a colour matching deposit and a regular hardness, even in the heat affected zone.

ind.12



= -	~ 40 V
-----	--------

**Liability:** This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.