



Selectarc HB Cavit

Electrode highly Resistant to Cavitation

Description & Applications

Synthetic basic coated electrode with high efficiency (160%), destined to surface all pieces subject to high impact, erosion and cavitation. Also used as cushion layer before hardfacing in case of heavy reclaiming. The deposit is austenitic and is exceptionally resistant to impact and wear. The high amount of Cr highly increases the resistance to corrosion.

General applications: Repairing of used pieces or protection of new pieces in hydro power stations, pistons of hydraulic presses, different types of turbines, valves, ...)

Base materials **Austenitic steels with high Mn , martensitic stainless steels:**

DIN 17145 and 17155 : X110Mn14
X4CrNi 13 4 1.4313 ; G-X5CrNiMo 13 4 1.4407

All Weld Metal Mechanical Properties


Hardness as welded	Hardness after work hardening
200-250 HB	400-500 HB
Obtained in pour weld metal	

Welding Current & Instructions

Electrode	ØxL (mm)	3,2x350	4,0x450
Current	(A)	110-130	130-160

Redrying 1h at 300°C, if necessary. Guide electrodes with a slight declination, weld with a short arc and prevent a high heat input in order to respect an interpass temperature of 250°C maximum. Do not preheat the piece to weld up to more than 100°C. Heat treatment depends on the base metal.

ind.13



Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.