



Selectarc HB25

Surfacing Electrode

Description & Applications

Rutile coated electrode for surfacing of equipment parts, constructions and tools, resistant to medium friction and compression. Good resistance to cavitation, highly resistant to shocks. Sound, crack free deposit, machinable with standard tools.

General applications: Surfacing of rails and switches, roller guides, slideways, build up before hardfacing.

All Weld Metal Mechanical Properties

Hardness
~ 250 HB
Obtained in pour weld metal

Welding Current & Instructions

Electrode	ØxL (mm)	2,5x350	3,2x450	4,0x450	5,0x450
Current	(A)	90	115	160	230

Preheating is not required on mild and medium carbon steels. Low alloyed, high carbon tool steels etc. have to be preheated to 200-400°C, depending on their composition and thickness. Slow cooling in still air after surfacing.

ind.13



= - ~ 45V

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.