



Selectarc HB600HT

*Hardfacing Electrode
For metal/metal wear*

Description & Applications

Rutile coated electrode with a Cr-Mo-C martensitic steel deposit, resistant to metal/ metal wear up to 550°C. For all pieces subject to hot or cold metal abrasion, even in the presence of shocks and pressure. As welded only machinable by grinding. Soft fusion, no spatters, self releasing slag.

General applications: Hardfacing of shear blades, moulds, pressing and forging dies.

All Weld Metal Mechanical Properties

Hardness
58–61 HRC
Obtained in pour weld metal

Welding Current & Instructions

Electrode	ØxL (mm)	2,5x350	3,2x350	4,0x450
Current	(A)	80	110	150

Redrying 1h at 250°C, if necessary. Low alloyed, high carbon tool steels etc. have to be preheated to 250-450°C, depending on their composition and thickness. Slow cooling in still air after surfacing.

ind.13



= + ~ 45V

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.