



# Selectarc HB64S

Coated Electrode for Surfacing  
In sugar mills

## Description & Applications

Electrodes with a high alloy content of elements which form carbides. Therefore especially used for hard facing of parts subject to high abrasion, friction and corrosion. The electrode is easy to weld, has a smooth drop transfer and only a negligible slag content, easy re-striking even on wet pieces. Recovery approx. 200%.

**General applications:** Especially designed for claddings in sugar mills , roughing or arcing of mill rollers for better gripping etc.

## All Weld Metal Mechanical Properties


Hardness  
~ 61 HRC

## Welding Current & Instructions

Electrode	ØxL ( mm )	3,2x350	4,0x450	5,0x450
Current	( A )	120-150	170-210	220-260

Hold a short arc and the electrode almost vertical. Select lowest amperage possible to keep dilution low and weave only slightly.

ind.13



= + ~50V



**Liability:** This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.