



Selectarc Inox 21/33Mn

High Temperature
Stainless Steels Electrode

Classification

ISO 3581-A : E Z 21 33 Mn Nb B 42

Description & Applications

Basic coated austenitic stainless steel electrode with 21%Cr ,33%Ni, 1.2%Nb and an increased manganese content , used to weld austenitic heat resistant alloys, castings and plates resisting to scaling and oxidation up to 1050°C. Regular and stable fusion, good slag removal, nice aspect of the bead.

Main applications: Chemical and Petrochemical industries.

Base materials

UNS	Alloy	EN	Material N°
N08800	800	X10NiCrAlTi32-20	1.4876
		G-X10NiCrNb32-20	1.4859
N08810		X5NiCrAlTi31-20	1.4958
N08811		X8NiCrAlTi32-21	1.4959

Typical Weld Metal Composition (%)

C	Si	Mn	Cr	Ni	Nb	Fe
0.12	0.5	4.5	21.0	33.0	1.0	Rem.

All Weld Metal Mechanical Properties


$R_{p0.2}$ (MPa)	R_m (MPa)	A_5 (%)
420	610	29

Welding Current & Instructions

Electrode	ØxL (mm)	2,5x300	3,2x350	4,0x350
Current	(A)	70	100	130

Redrying 2 hours at 250°C, if necessary. Interpass temperature : <150°C.

ind.12



Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.