



Selectarc Inox 2209

*Stainless Electrode
For Duplex Steels*

Classification

AWS A 5.4 : E2209-17 EN 1600 : E 22 9 3 N L R 3 2
ISO 3581-A : E 22 9 3 N L R 3 2

Description & Applications

Rutile-basic electrode with an austenitic- ferritic microstructure (duplex). The weld metal can be applied for operation temperatures up to 250°C and is resistant in chloride containing media, like sea water, against pitting corrosion as well as crevice and stress corrosion. Easy to weld in all positions, except vertical down. Stable arc, regular drop transfer, easy slag removal, finely rippled weld beads.

Main applications : For butt welding and cladding of steels and castings with an austenitic - ferritic structure, which are used for pumps, vessels, piping systems etc. attacked by chloride containing solutions. But also for impellers and other components which require high strength combined with corrosion attack.

Base materials

UNS	Alloy	EN 10088	Material N°	CLI
S31803		X2CrNiMoN22-5-3	1.4462	URANUS 45N
S32304	35N	X2CrNi23-4	1.4362	
S32900	329	X3CrNiMoN27-5-2	1.4460	
		G-X8CrNiN26-7	1.4347	
		G-X6CrNiMo24-8-2	1.4463	

Typical Weld Metal Composition (%)

C	Si	Mn	Cr	Ni	Mo	N	Fe
<0.030	0.9	0.9	22.5	9.0	3.0	0.18	Rem.

All Weld Metal Mechanical Properties

R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	KV (J)	
>550	>700	>22	+20°C	>50
			-40°C	>37

Welding Current & Instructions

Electrode	ØxL (mm)	2,5x300	3,2x350	4,0x350
Current	(A)	50-75	70-100	90-150

Redrying 2-3 hours at 250-300 °C. Guide electrodes with a slight declination and weld with a short arc. Interpass temperature : <150°C.

ind.12



= + ~ 70V

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.