



# Selectarc Ni182

*Basic coated  
Inconel type Electrode*

## Classification

AWS A5.11 : ENiCrFe-3  
UNS : W86182

ISO 14172 : E-Ni 6182 (NiCr15Fe6Mn)  
Material N° : 2.4620

## Description & Applications

Basic coated electrode with an NiCrFe type nickel base deposit. Used for repairing and joining of Nickel alloys, 5 % Nickel steels, cryogenic stainless steels (down to  $-196^{\circ}\text{C}$ ), Incoloy 800 and other high temperature steels. For joining dissimilar materials as stainless steels to low alloyed steels, stainless steels to Nickel alloys, for buttering of difficult to weld steels. Deposit insensitive to cracks, very good resistance against acids, salt and alkaline solutions, molten salt. Resistant in oxidizing and carburizing atmospheres ( avoid a sulphurous atmosphere).

**Main applications:** Oven parts, burners, heat treatment equipment, cement works , moulds, tanks, transport and storage of liquid gas. Chemical industries, petrochemical industries, glassworks, civil engineering, repairing and maintenance workshops.

Note: "Inconel" and "Incoloy" are registered trade names of Inco Alloys.

### Base materials

UNS	Alloy	DIN	Material N°
N06600	600	NiCr15Fe	2.4816
N08800	800	X10NiCrAlTi3220	1.4876
N08810	800H	X5NiCrAlTi3120	1.4958
	DS	X8NiCrSi3818	1.4862

## Typical Weld Metal Composition ( % )

C	Si	Mn	Cr	Nb	Fe	Mo	Ni
<0.04	0.4	6.0	16.5	2.0	6.0	0.2	Rem.

## All Weld Metal Mechanical Properties


$R_{p0.2}$ ( MPa )	$R_m$ ( MPa )	$A_5$ ( % )	KV ( J )	
>380	>620	>35	+20°C	>80
			-196°C	>65

## Welding Current & Instructions

Electrode	ØxL ( mm )	2,5x300	3,2x350	4,0x350	5,0x450
Current	( A )	50-70	70-95	90-120	120-160

Redrying 1 h at  $250-300^{\circ}\text{C}$ . Joints to weld must be clean, exempt from grease, cracks. Guide electrodes with a slight declination, weld with a short arc and prevent a high heat input by applying the stringer bead technique ( weaving max. 2-3 times core wire diameter ).

ind.12



**Liability:** This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.