



Selectarc Ni190

Basic coated NiCu type Electrode

Classification

AWS A5.11 : ENiCu-7 ISO 14172 : E-Ni 4060 (NiCu30Mn3Ti)
 UNS : W84190 Material N° : 2.4366

Description & Applications

Basic coated electrode with a Monel* type Nickel-Copper deposit designated for butt welding and surfacing of Nickel-copper, Copper-Nickel and Copper-Nickel plated steels. Also recommended for dissimilar joining like steels to Nickel-Copper or steel to Copper / Copper-Nickel. Excellent resistance to stress corrosion in Cl- containing environments.

Main applications: Construction of equipment for the chemical industry and petrochemical industry, naval constructions and installations for sea water desalination.

Note: "Monel" is a registered trade name of Inco Alloys.

Base materials

UNS	Alloy	DIN	Material N°
C70600	CuNi90/10	CuNi10Fe1Mn	2.0872
C71500	CuNi70/30	CuNi30Mn1Fe	2.0882
N04400	400	NiCu30Fe	2.4360
N05500	K-500	NiCu30Al	2.4375

Typical Weld Metal Composition (%)

C	Si	Mn	Fe	Ti	Cu	Ni
<0.05	0.7	3.2	1.2	0.5	29	Rem. (≥ 65)

All Weld Metal Mechanical Properties


R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	KV (J)
>300	>480	>30	+20°C >80

Welding Current & Instructions

Electrode	ØxL (mm)	2,5x300	3,2x350	4,0x350
Current	(A)	50-75	80-110	90-130

Redrying 2 h at 250°C. Joints to weld must be clean, exempt from grease, cracks. Guide electrodes with a slight declination (10-20° inclined in direction of travel), weld with a short arc and prevent a high heat input by applying the stringer bead technique (weaving max. 2 times core wire diameter).

ind.12



Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.