



Selectarc NiTi3

Pure Nickel Electrode

Classification

AWS A5.11 : ENi-1
Material N° : 2.4156

ISO 14172 : E-Ni 2061 (NiTi3)

Description & Applications

Basic coated electrode with a Nickel deposit containing 1-2%Ti designated for butt welding of pure Nickel (alloy 200) and surfacing of Nickel-copper, Copper-Nickel and Copper-Nickel plated steels. Also recommended for dissimilar joining like steels to Nickel-Copper or steel / Copper to Copper-Nickel. Excellent resistance to NaOH up to 400°C.

Main applications: Construction of equipment for the chemical industry and petrochemical industry, food stuff industry. For caustic soda production as well as for soap and detergents.

Base materials

UNS	Alloy	DIN	Material N°
N02200	200	Ni99.2	2.4066
N02201	201	LC-Ni99	2.4068
N02205	205	LC-Ni99.6	2.4061
		Ni99.6	2.4060

Typical Weld Metal Composition (%)

C	Si	Mn	Fe	Ti	Al	Ni
<0.03	0.7	0.3	0.3	1.6	0.3	Rem.

All Weld Metal Mechanical Properties


R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	KV (J)	
>280	>420	>28	+20°C	>160
			-196°C	>160

Welding Current & Instructions

Electrode	ØxL (mm)	2,5x350	3,2x350	4,0x350
Current	(A)	70-90	90-120	120-160

Redrying 1 h at 250-300°C. Joints to weld must be clean, exempt from grease, cracks. Guide electrodes with a slight declination (10-20°) inclined in direction of travel), weld with a short arc and apply the stringer bead technique (weaving max. 2 times core wire diameter). To improve degassing of the deposit, adopt a low welding speed.

ind.12



Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.