



# Selectarc 307B

*High manganese stainless  
Basic coated Electrode*

## Classification

AWS A5.4 : ~E307-15

EN 1600 : E 18 8 Mn B 3 2

ISO 3581-A : E 18 8 Mn B 3 2

## Description & Applications

Austenitic (non-magnetic) basic coated stainless steel electrode for joining and overlaying on manganese steels (up to 14% Mn) and high sulphur and phosphorus containing steels, also for joining dissimilar steels, construction steels to stainless steels, for cushion layers prior hardfacing. Repairing of pieces submitted to shocks or wear by friction. Stable arc ease of use, good slag removal, nice aspect of the beads.

**Main applications:** For civil engineering, railways, cement works (screening steels, digger buckets, crusher jaws...)

### Base materials

**Screening steels**

**Tools steels\***

**Low alloyed steels\***

**Austenitic steels with Mn:** type Z 120 M 12, X 120 Mn 12, 1.3401

**Spring steels:** 45 Cr 4, 1.7035, 46 Si 7, 1.5024, 51 Si 7, 1.5025, 56 Si 7, 1.5026

**Stainless steels to low alloyed steels**

(\*) with eventual pre- and post weld heat treatment.

## Typical Weld Metal Composition ( % )

C	Si	Mn	Cr	Ni	Fe
0.1	0.4	6	18.0	8.0	Rem.

## All Weld Metal Mechanical Properties

R <sub>p0.2</sub> ( MPa )	R <sub>m</sub> ( MPa )	A <sub>5</sub> ( % )	KV ( J )
>400	600-750	>35	+20°C >90


Hardness: as welded ~ 200 HB, work hardened ~ 500 HB.

## Welding Current & Instructions

Electrode	ØxL ( mm )	2,5x300	3,2x350	4,0x350	5,0x450
Current	( A )	65	90	120	150

Redrying at 300°C during 1 hour. Never preheat Mn-steels because of its sensitivity to hot cracks.

ind.12



**Liability:** This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.