



Selectarc Al105

Aluminium Electrode with 5% Si

Classification

AWS A5.3 : E4043 DIN 1732 : EL-AISi5
 UNS : A94043 Material N : 3.2245

Description & Applications

Aluminium electrode with 5%Si for welding and repairing aluminium or aluminium alloy pieces (AlSi, AlCuSiMn, AlSiMg, AlZnMg...). For joints between aluminium and aluminium-alloys, as well as for aluminium castings.

Main applications: Engine blocks, cylinder heads, tanks, containers, frames, lorry tipper.

Base materials

DIN	Material N°
G-AISi6Cu4	3.2151
AlMgSi1	3.2315
G-AISi5Mg	3.2341
G-AISi7Mg	3.2371
AlMgSi0,5	3.3206
AlMgSi0,7	3.3210
AlMg1SiCu	3.3211

Typical Weld Metal Composition (%)

Si	Mn	Fe	Al
5.0	<0.5	<0.5	Rem.

All Weld Metal Mechanical Properties

R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
70-100	110-160	>15	~50 HB


Welding Current & Instructions

Electrode	ØxL (mm)	2,5x350	3,2x350	4,0x350
Current	(A)	60	90	120

Clean the weld zone; preheat massive pieces (more than 6mm of thickness) to 150-250°C. In order to avoid all risks of porosity, weld with a short arc and guide the electrode at 90° to the piece to be welded. Use a fast travel speed, remove slag between passes and when finished.

Warning! Aluminium electrodes are very sensitive to humidity pick-up; therefore keep the opened tins in a dry place. In case of humidity pick-up dry the electrodes 3h/100°C.

ind.12



Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.