



Selectarc Co1

*“Grade 1” type cobalt base
Hardfacing Electrode*

Description & Applications

Hardfacing electrode with a rutile-basic coating. Cobalt based deposit of « stellite grade 1 » type (Co-Cr-W). Hardest Selectarc Co-type (superior to all other types of stellite). Very good resistance to metal-metal wear and to corrosion up to 800°C. Coefficient of friction very low. Highly resistant to erosion and cavitation.

General applications: Hardfacing of rollers, rails, bearing and shafts of pumps, extrusion nozzles, hot cutting tools, conveyor screws.

* Note : "Stellite" is a trade mark of Deloro Stellite (Haynes International)

All Weld Metal Mechanical Properties

Hardness (as welded) +20°C
53-57 HRC

Hardness (as welded) +600°C
42-45 HRC

Welding Current & Instructions

Electrode	ØxL (mm)	3.2x350	4,0x350	5,0x450
Current	(A)	100	140	180

Redrying 1h at 250°C, if necessary. Preheat massive pieces 250-400°C. Use a low welding current in order to limit the dilution with the base metal and to achieve the hardness of this alloy. Cool down slowly in order to limit the risks of cracks in the deposit. Weld eventual cushion layers with Selectarc 307 R or 29/9.

ind.13



= + ~ 70V



Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.