



Selectarc Co21S

*Cobalt base Hardfacing
Electrode "Grade 21" type*

Description & Applications

Hardfacing electrode with a rutile-basic coating. Cobalt base deposit of « stellite grade 21 » type (Co-Cr-Mo-Ni). Deposit characterised by a good metal-metal wear and oxidation resistance up to 1000°C, even in presence of sulphurous atmosphere. Good behaviour to important thermal and mechanical shocks, excellent resistance to cracks, highly resistant to cavitation and erosion, deposit non-magnetic.

General applications: Surfacing of motor valves, gas turbine blades, extrusion nozzles, forging dies, forging tools, mixers, valves for gas/water/vapour/acids.

* Note : "Stellite" is a trade mark of Deloro Stellite (Haynes International).

All Weld Metal Mechanical Properties

Hardness (as welded) +20°C
32-38 HRC

Hardness (as welded) +600°C
250-300 HB

Welding Current & Instructions

| | | | | |
|-----------|------------|---------|---------|---------|
| Electrode | ØxL (mm) | 2,5x350 | 3,2x350 | 4,0x350 |
| Current | (A) | 75 | 100 | 140 |

Redrying 1h at 250°C, if necessary. Preheat massive pieces 250-400°C. Keep this temperature during welding, cool down slowly to reduce the risk of cracks while cooling. Weld eventual cushion layers with Selectarc B 90.

ind.13



= + ~ 70V



Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.