



Selectarc Inox 25/35H

High Temperature
Stainless Steel Electrode

Classification

ISO 3581-A : E Z 25 35 Nb H B 4 2

Description & Applications

Basic coated austenitic stainless steel electrode with 26%Cr ,35%Ni, 1.2%Nb and an increased carbon content. Used to weld austenitic heat resistant alloys, centrifugally cast tubes etc. resisting to scaling and oxidation up to 1200°C. Regular and stable fusion, good slag removal, nice aspect of the bead.

Main applications: Petrochemical industry, for welding centrifugally cast pyrolysis coils, reformer tubes, piping systems.

Base materials

UNS	Alloy	EN	Material N°
J93503		G-X40CrNiSi25-12	1.4837
J94204	HK40	G-X40CrNiSi25-20	1.4848
N08705	HP45	G-X40NiCrSi35-25	1.4857
		G-X40NiCr38-18	1.4849
		G-X40NiCrNb35-25	1.4852

Typical Weld Metal Composition (%)

C	Si	Mn	Cr	Ni	Nb	Fe
0.4	1.0	1.8	26.0	35.0	1.2	Rem.

All Weld Metal Mechanical Properties


$R_{p0.2}$ (MPa)	R_m (MPa)	A_5 (%)
>440	>660	>12

Welding Current & Instructions

Electrode	ØxL (mm)	2,5x300	3,2x350	4,0x350
Current	(A)	70	100	135

Redrying 2 hours at 250°C, if necessary. Interpass temperature : <150°C.

ind.12



Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.